

# HAYNES<sup>®</sup> 617 alloy

## Hardness and Grain Size

<b>Form</b>	<b>Hardness</b>	<b>Typical ASTM Grain Size</b>
Sheet	88 HRBW	3 - 4.5
Plate	91 HRBW	3 - 5
Bar	88 HRBW	3 - 4.5

All samples tested in solution-annealed condition.

HRBW = Rockwell Hardness "B", Tungsten Indentor.

[Print Page](#)