

HAYNES[®] 188 alloy

Impact Strength Properties

Test Temperature		Typical Charpy V-Notch Impact Resistance	
°F	°C	ft.-lbs	J
-300	-185	116	158
-150	-100	131	178
70	20	143	194
1000	540	117	159
1300	705	107	145

*Average of longitudinal and transverse tests on solution-annealed plate

[Print Page](#)

[Download Page](#)