

# HASTELLOY<sup>®</sup> X alloy

## Formability

### Sheet

Condition	Typical Olsen cup Depth	
	in.	mm
-		
Heat-treated at 2150°F(1177°C), Rapid Cooled	0.48	12.3