

# ULTIMET<sup>®</sup> alloy

## Impact Strength

These impact strengths were generated using Charpy V-notch samples, machined from mill annealed plate of thickness 12.7 mm (0.5 in).

Test Temperature		Impact Strength	
°F	°C	ft-lbf	J
RT	RT	130	176
-40	-40	125	169
-80	-62	119	161
-320	-196	68	92

RT= Room Temperature