

HASTELLOY[®] C-276 alloy

Impact Strength

Type of Test	Test Temperature	Form	Thickness		Impact Strength	
			in	mm	ft.lbf	J
Charpy V-Notch	RT	Plate	0.394	10	348	472
Charpy V-Notch	RT	Plate	0.472	12	351	476

RT= Room Temperature

[Print Page](#)