

MULTIMET[®] alloy

Hardness

| Form | Hardness, HRBW | Typical ASTM Grain Size |
|-------------|---------------------------|--------------------------------|
| Sheet | 90 | 4.5 - 6.5 |
| Plate | 92 | 3 - 6.5 |
| Bar | 89 | 3 - 5 |

HRBW = Hardness Rockwell "B", Tungsten Indentor.

All samples tested in solution-annealed condition

[Print Page](#)