

# HAYNES<sup>®</sup> 263 alloy

## Aged Hardness

### Age Hardened Room Temperature Hardness

<b>Form</b>	<b>Hardness</b>
Sheet	26 HRC
Plate	27 HRC

Mill Annealed +1472°F/8h/Air Cool

HRC = Rockwell Hardness "C"