

HAYNES[®] 263 alloy

Aged Hardness

Age Hardened Room Temperature Hardness

Form	Hardness
Sheet	26 HRC
Plate	27 HRC

Mill Annealed +1472°F/8h/Air Cool

HRC = Rockwell Hardness "C"