

# HASTELLOY<sup>®</sup> X alloy

## Hardness and Grain Size

### Room Temperature Hardness of Material Solution Annealed at 2150°F

<b>Form</b>	<b>Hardness, HRBW</b>	<b>Typical ASTM Grain Size</b>
Sheet	86	3 - 5
Plate	87	3.5 - 6
Bar	88	2 - 5

HRBW = Hardness Rockwell "B", Tungsten Indentor.