

HAYNES[®] 214[®] alloy

Hardness

	Typical ASTM Grain Size	Average Hardness, HRBW
Plate	3.5 - 5	100
Bar	2.5 - 5.5	94
Sheet	3.5 - 5	98

HRBW = Hardness Rockwell "B", Tungsten Indentor.