

HASTELLOY[®] G-30[®] alloy

Impact Strength

Plate Thickness		Test Temperature		Impact Strength*	
in	mm	°F	°C	ft.lbf	J
0.5	12.7	RT	RT	260	353
0.5	12.7	-320	-196	262	355

*Transverse Charpy V-Notch Samples

RT=Room Temperature