

HAYNES[®] HR-120[®] alloy

Hardness and Grain Size

Solution-annealed Room Temperature Hardness

| Form | Hardness, HRBW | Typical ASTM Grain Size |
|-------------|-----------------------|--------------------------------|
| Sheet | 88 | 3.5 - 5 |
| Plate | 87 | 0 - 5 |
| Bar | 84 | 0 - 4.5 |

HRBW = Hardness Rockwell "B", Tungsten Indentor.

[Print Page](#)