

MULTIMET[®] alloy

Impact Strength

Test Temperature		Charpy Impact Strength	
°F	°C	ft-lb	J
1500	816	69	94
RT	RT	113	153
-20	-29	105	142
-108	-78	86	117
-216	-138	66	89
-321	-196	56	76

All samples were in solution annealed condition.

RT = Room Temperature