

HASTELLOY[®] C-2000[®] alloy

Impact Strength

Plate Thickness		Test Temperature		Impact Strength*		Number of Tests
in	mm	°F	°C	ft.lbf	J	
0.5	12.7	RT	RT	333	451	3
0.5	12.7	-320	-196	407	552	3
1.75	44.5	RT	RT	343	465	3
1.75	44.5	-320	-196	412	559	3

*Charpy V-Notch Samples

RT= Room Temperature