









## 11. TOXICOLOGICAL INFORMATION

<b>TOXICITY DATA</b>	Eye: Rabbit (cobalt) unknown amount produced severe reaction with abscess involving lens, ciliary body, vitreous humor, and retina.
	Skin: No data.
	Ingestion: Guinea Pig (nickel): LD <sub>Lo</sub> : 5 mg/kg Rat (cobalt): LD <sub>50</sub> : 6171 mg/kg Rabbit (cobalt): LD <sub>50</sub> : 750 mg/kg Human (copper): TD <sub>Lo</sub> : 120 µg/kg affects the gastrointestinal tract (nausea or vomiting). Human (chromium): LD <sub>Lo</sub> : 71 mg/kg Rat (Iron): LD <sub>50</sub> : 30,000 mg/kg Rat (manganese) LD <sub>50</sub> : 9,000 mg/kg Rat (Titanium): LD <sub>50</sub> : >5,000 mg/kg
	Inhalation: Rabbit (nickel): TC <sub>Lo</sub> : 130 µg/m <sup>3</sup> 35 weeks (intermittent-6 hours) Pig (cobalt) TC <sub>Lo</sub> : 100 µg/m <sup>3</sup> /6 hours for 13 weeks - (intermittent) Human (chromium VI): TC <sub>Lo</sub> : 110 µg/m <sup>3</sup> 3 years (continuous) tumorigenic (carcinogenic per RTECS) Human (manganese): TC <sub>Lo</sub> : 2,300 µg/m <sup>3</sup>
	Subchronic: Rat (molybdenum) inhalation: 12-16 g/m <sup>3</sup> /1 hour/30 days, resulted in slight growth depression, and thickening of the intraaveolar septa, which contained connective tissue fibers.
Other: Intravenous; Dog (nickel) LD <sub>Lo</sub> : 10 mg/kg Implant; Rat (chromium) TD <sub>Lo</sub> : 1200 µg/kg intermittent over 6 weeks. Rat (cobalt) intramuscular: 126 mg/kg, tumorigenic at site of application.	
<b>CHRONIC/ CARCINOGENICITY (See Table 4)</b>	Teratology: Rat (molybdenum) oral: 5800 µg/kg given to female 30 weeks prior to mating and during days 1-20 of pregnancy caused specific musculoskeletal system development abnormalities.
	Reproduction: Rat (cobalt) unspecified exposure route, 0.05 mg/kg continuous, administered throughout gestation to female was embryotoxic.
	Mutagenicity: Hamster (chromium III) lung cell: 34 mg/L caused sister chromatid exchange. Human (cobalt) DNA damage: Human Leukocyte 3 mg/L. Human (Chromium VI) DNA damage: Human Leukocyte 50 µmol/L.

## 12. ECOLOGICAL INFORMATION

In solid form this material poses no special environmental problems. Metal powders, fumes, or dusts may have significant impact on air and water quality. Airborne emissions, spills, and releases to the environment (discharge to streams, sewer systems, ground water, surface soil, etc.) should be controlled immediately.

Ecotoxicity: Few plants accumulate cobalt at greater than 100 ppm, the level at which severe phytotoxicity would occur. There is little tendency for chromium III bioaccumulation along the food chain.

Molybdenum: (fathead minnow), LC<sub>50</sub>: 370 mg/L/96 hours. Terrestrial plants can contain enough molybdenum to be toxic to animals but still grow normally.

Environmental Degradation: In water, cobalt is adsorbed greatly to hydrolysate or oxidate sediments. It may be taken into solution in small amounts through bacteriological activity. In water, chromium III oxide is expected to eventually precipitate to sediments. In air, chromium III oxide is primarily removed by fallout and precipitation. Soils with a high chromium content (>0.2%) are expected to be infertile. The half-life of chromium in soils may be several years.

## 13. DISPOSAL CONSIDERATIONS

WASTE DISPOSAL: Whenever possible, recover scrap for reuse or recycling. If necessary, dispose of waste material in accordance with local, state, or federal regulations. P501 For specific labeling, packing, storage, transportation, and disposal procedures, contact an Environmental Engineer or consultant familiar with waste disposal regulations.

#### 14. TRANSPORT INFORMATION (Not Meant to be All Inclusive)

As a wrought product, these alloys are not regulated by the U.S. Department of Transportation (DOT) and the International Air Transport Association (IATA). The following information should be used by individuals with "Function-specific Training" required by 49 CFR 172.704, and Dangerous Goods Regulations published by the International Air Transport Association (IATA).

SHIPPING NAME	If alloy dust or powder is created, it may be a flammable solid or spontaneously combustible material (DOT hazard class 4.1 and 4.2, respectively). A sample of metal powder should be tested according to the U.N. manual of tests and criteria. See 49 CFR 173.124 (a) and (b).
IDENTIFICATION NUMBER	Not Available (Determine by test results)
HAZARD CLASS	Not Available (Determine by test results)
LABEL(S) REQUIRED	Not Available (Determine by test results)

#### 15. REGULATORY INFORMATION

U.S. FEDERAL REGULATIONS	<b>OSHA:</b> Listed as air contaminants (29 CFR 1910.1000). Hazardous by definition of Hazard Communication Standard (29 CFR 1910.1200).
	<b>TSCA</b> (Toxic Substance Control Act): Components of this material are listed on the TSCA inventory.
	<b>CERCLA:</b> Hazardous Substance (40 CFR 302.4): Chromium, Copper, Nickel.  Extremely Hazardous Substance (40 CFR 355): Not Listed
	<b>SARA HAZARD CATEGORY:</b> Listed below are the hazard categories for Sections 311 and 312 of the Superfund Amendment and Reauthorization Act of 1986 (SARA Title III):
	Immediate Hazard: X Delayed Hazard: X Fire Hazard: - Pressure Hazard: - Reactivity Hazard: -
	<b>Chemicals subject to the reporting requirements of Section 313 or Title III of SARA and 40 CFR Part 372:</b> Aluminum (as a fume or dust), cobalt, chromium, copper, manganese, nickel.
U.S. STATE REGULATIONS	California's "Safe Drinking Water and Toxic Enforcement Act of 1986" (Proposition 65)  During welding, and thermal cutting these products may produce cobalt oxide, nickel compounds, and hexavalent chromium compounds which are known to the State of California to cause cancer and birth defects. State of California, Health and Welfare Agency, 1600 Ninth Street, Room 450, Sacramento, CA 95914, Telephone (961) 455-6955.
	Pennsylvania Worker and Community Right to Know: Aluminum, Cobalt, Copper, Chromium, Manganese, Nickel, and Vanadium (fume or dust) are designated environmental hazards on the Hazardous Substance List. Title 34, Part XIII, Chapter 323.
INTERNATIONAL REGULATIONS	<b>Labeling in Accordance with the GHS</b> The following hazard classification and risk phrases required by the GHS apply to dust and particulate created by these products. Danger: May cause allergy or asthma symptoms or breathing difficulties if inhaled, Category 1.

Warning: May cause an allergic skin reaction, Category 1.  
 Warning: causes skin irritation, Category 2.  
 All products except: HASTELLOY® HYBRID-BC1®, HASTELLOY G-35®, HAYNES® 242®, HAYNES® 625-, HAYNES® 718-, HAYNES® X-750-, HAYNES® 625(Low Iron)-alloy, 601-, I-36-, M-400-, M-413-, N- 61-, NFE 258- NIT 32-, NIT 50-, NIT 60-, 17/7 PH-, 20CB3- 52-, 72-, 80/20-, 80/20 Cb-, 95/5-, 200 alloy, and all alloys listed on page 10:  
 Warning, Harmful if swallowed, acute toxicity Category 4.

**Canada WHIMS** These products have been classified in accordance with the hazard criteria of the CPR, and the SDS contains all of the information required by the CPR.

**16. OTHER INFORMATION**

**SDS STATUS**

This SDS replaces the December 31, 2013 revision for steel wire & rod. Sections 1, 2, 4, 8, 10, 15, and 16 have been changed.

The above information has been prepared by CB&I, Inc., under contract with Haynes International and is a compilation of information from various sources believed to be accurate. As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any material described herein. Information contained herein is believed to be true and accurate, but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable Federal, State, Provincial, and local laws and regulations remain the responsibility of the user.

Portions of this document were authored by Teledyne McKay Co. and are used with permission.

## LABEL INFORMATION

### Structural Wire

HASTELLOY® HYBRID-BC1®, HASTELLOY® B-3, HASTELLOY® C-4, HASTELLOY® C-22®, HASTELLOY® C-22®HS, HASTELLOY® C-276, HASTELLOY® C-2000®, HASTELLOY® G-30®, HASTELLOY® G-35®, HASTELLOY® N, HASTELLOY® S, HASTELLOY® W, and HASTELLOY® X-alloy.

HAYNES® C263, HAYNES® GTD222, HAYNES® HR-120®, HAYNES® HR-160®, HAYNES® HR-224®, HAYNES® NS-163®, HAYNES® Waspaloy, HAYNES® X-750, HAYNES® 25, HAYNES® 92, HAYNES® 188, HAYNES® 214®, HAYNES® 214®W, HAYNES® 230®W, HAYNES® 242®, HAYNES® 282®, HAYNES® M418, HAYNES® 556®, HAYNES® 625, and HAYNES® 718 alloy,

I-36, L605, M-400, M-413, MULTIMET®, N 61, NFE 258, NIT 32, NIT 50, NIT 60, MP35N, ULTIMET®, 17/7 PH, 20, 20CB3, 52, 72, 80/20, 80/20 CB, 95/5, 200, 202, 302, 302 HQ, 302 MO, 302 N, 302 NC, 302 V, 304, 304 L, 304 V, 305, 308 L, 316, 316 LVM, 316 L, 320, 347, 416, 420, 420 VMH, 420 VML, 420 DVM, 420 NWH, 430, 455, 600, 601, 622, 800, 825, and 875-alloy,

The following hazard classification and risk phrases required by the Globally Harmonized System (GHS) apply **only** when these products create dust and particulate when subjected to cutting, grinding, machining, crushing, or similar operations.

**Danger:** May cause allergy or asthma symptoms or breathing difficulties if inhaled.

**Warning:** May cause an allergic skin reaction.

**Warning:** Causes skin irritation.

**Warning: Harmful if swallowed, acute toxicity.** All products except: HASTELLOY® HYBRID®-BC1, HASTELLOY®G-35®, Haynes® 92, Haynes® 182, Haynes® 242, Haynes® 625, Haynes® 718, Haynes® X-750, Haynes® 625(Low Iron)-alloy, 601, I-36, M-400, M-413, N- 61, NFE 258, NIT 32, NIT 50, NIT 60, 17/7 PH, 20CB3, 52, 72, 80/20, 80/20 CB, 95/5, 200 alloy, and all alloys listed on page 9 of the Safety Data Sheet (SDS):



**DANGER WARNING**

Do not eat, drink, or smoke when using this product. Avoid breathing dust or fume. Wear safety glasses. Cut-resistant gloves and respiratory protection may be required for specific jobs. Wash hands thoroughly after touching dust created by these products.

If exposed or concerned, get medical advice. Whenever possible recover alloys for reuse or recycling. If necessary, dispose of waste material in accordance with local, state or federal regulations.

**First Aid:** (The following instructions apply only to dust and welding fume forms of the product)

**Inhalation:** Breathing difficulty caused by inhalation of dust or fume requires removal to fresh air. If breathing has stopped, perform artificial respiration and obtain medical assistance at once.

**Ingestion:** Never give anything by mouth to an unconscious person. Contact a poison control center. Unless the poison control center advises otherwise, have that conscious person slowly drink 1 to 2 glasses of water to dilute, inducement of vomiting is not necessary. Obtain medical assistance at once.

**Skin:** Skin cuts and abrasions can be treated by standard first aid. Quickly remove contaminated clothing but do not shake clothing. Skin contamination with dust or powder can be removed by washing with soap and water. If irritation or reddened, blistered skin occurs, obtain medical assistance.

**Eyes:** Do not allow victim to rub or keep eyes tightly shut. Dust or powder should be flushed from the eyes with copious amounts of clean water, for at least 15 minutes, or until transported to an emergency medical facility. Consult a physician at once.

**Notice:** INHALATION OF DUST MAY CAUSE SERIOUS LUNG INJURY. SKIN, EYE, AND MUCOUS MEMBRANE IRRITATION MAY OCCUR.

- The products identified on the Haynes® International SDS HW-7032 may contain, in varying concentrations, the following elemental constituents: aluminum, cobalt, chromium, copper, iron, manganese, molybdenum, nickel, titanium, and tungsten. For specific concentrations of these and other elements present, refer to the Safety Data Sheet (SDS) for this product.
- Inhalation of metal dust or fume generated from cutting, grinding, melting, or machining these alloys may cause adverse health effects such as reduced lung function, nasal, and mucous membrane irritation. Exposure to dust generated by the use of these alloys may also cause eye irritation, skin rash, and effects on other organ systems.
- Avoid breathing dust or fume. If the use of this material produces dust or fume, use appropriate ventilation controls, personal protective equipment, or both. For additional information refer to the Safety Data Sheets (SDS H2071 and H1072) for these products.

**HAYNES**  
Wire Company

Safety Department, P.O. Box 677, 158 North Egerton Road  
Mountain Home, NC 28758-0677  
North America (NA) Information: 1- 828-692-5791  
Europe (EU) Information: 011-44-161-230-7777



Table 1 Structural Wire Products

ALLOY	AWS/UNS	Normal Composition, Weight Percent												
	Alloy No.	Ni▲	Co▲	Cr▲	Mo	W	Fe	Si	Mn▲	Al▲	Ti	Cu▲	B	Others (V▲)
HASTELLOY® HYBRID-BC1® alloy	2362**	62	--	15	22	--	2*	0.08*	0.25	0.5*	--	--	--	
HASTELLOY® B-3® alloy	N10675	65	3	<3	30	3	<3	0.1	<3	<1	<1	<1	--	
HASTELLOY® C-4 alloy	N06455	65	2*	16	16	0.5*	3*	0.08*	<1	--	0.7*	0.5*	--	--
HASTELLOY® C-22® alloy	N06022	56	2.5*	22	12	13	3	0.02	0.5*	--	--	0.5*	--	V-0.35*
HASTELLOY® C-22HS® alloy	2321**	61	1*	21	17	1*	2*	0.08*	0.8*	0.5*	--	0.5*	0.006*	--
HASTELLOY® C-86 alloy	N06686	55	--	21	16	3.7	2*	0.08*	0.75*	0.5*	0.14	--	--	--
HASTELLOY® C-276 alloy	N10276	57	2.5*	16	16	3	5	0.08*	<1	--	--	0.5*	--	V-0.35*
HASTELLOY® C-2000® alloy	N06200	59	2*	23	16	--	3*	0.08*	0.5*	0.5*	--	1.6	--	--
HASTELLOY® G-30® alloy	N06030	43	5*	30	5.5	2.5	15	0.8*	1.5*	--	--	2	--	Cb-0.8
HASTELLOY® N alloy	N10003	71	<1	7	17	<1	<5	<1	<1	--	--	<1	--	V-<1
HASTELLOY® G-35® alloy	N06035	58	<1	33.2	8.1	0.6*	2*	0.6*	0.5*	0.4*	--	0.3*	--	--
HASTELLOY® S alloy	N06635	67	2*	16	15	<1	3*	0.4	0.5	0.25	0.35*	--	0.015*	La-0.02
HASTELLOY® W alloy	N10004	63	2.5*	5	24	<1	6	<1	<1	--	--	0.5*	--	V- <0.6*
HASTELLOY® X alloy	N06002	47	1.5	22	9	0.6	18	<1	<1	<0.5	0.15*	0.5	0.008*	Cb-0.5*
HAYNES® C-263 alloy	N07263	52	20	20	6	--	0.7*	0.2	0.4	0.6*	2.4*	0.2*	0.005*	Zr-0.04*, (Al+Ti)-2.6
HAYNES® GTD222 alloy	2220**	50	19	22.5	<1	2	<1	0.25*	0.1*	1.3	2.3	0.1*	0.004	Cb-0.8, Ta-1
HAYNES® HR-120® alloy	N08120	37	3.0	25	<1	<0.5	33	0.6	0.7	0.1	0.2*	<0.5	<0.1	Cb-0.7
HAYNES® HR-160® alloy	N12160	37	29	28	<1	<1	3.5*	2.75	1*	0.4	0.5	0.5*	-	Cb+Ta-0.3*
HAYNES® HR-224® alloy	2224**	47	2*	20	0.5*	0.5*	27.5	0.3	0.5*	3.8	0.3	--	0.004*	Cb-0.15*, La-0.01*, Zr-0.025*
HAYNES® HR-235™ alloy	2431	57	1.1*	31	5.6	-	1.5*	0.4	0.5	0.3	-	3.8	-	--
HAYNES® NS-163® alloy	1630**	8	40	28	--	--	21	0.5*	0.5*	0.5*	1.3	--	0.015*	Cb-1
HAYNES® Waspaloy alloy	N07001	58	13.5	19	4.3	--	2*	0.1*	0.1*	1.5	3	0.1*	0.006	Zr-0.04*
HAYNES® X-750 alloy	N07750	70 <sup>b</sup>	1*	16	--	--	8*	0.35*	0.35*	0.8	2.5*	0.5*	--	Cb+Ta-1

Table 1 Structural Wire Products (continued)

AWS/UNS		Normal Composition, Weight Percent												
ALLOY	Alloy No.	Ni▲	Co▲	Cr▲	Mo	W	Fe	Si	Mn▲	Al▲	Ti	Cu▲	B	Others (V▲)
HAYNES® 25 alloy	R30605	10	51	20	<1	15	3*	0.4*	1.5	--	--	--	--	--
HAYNES® 92 alloy	N0709	>67	--	16	--	--	<8	<1	2	--	3	<1	--	
HAYNES® 625 (low iron)	2653**	62	<1	21	9	--	0.75*	0.5*	0.5*	0.4*	0.4*	0.5*	--	Cb+Ta-3.7
HAYNES® 188 alloy	R30188	22	39	22	--	14	3*	0.35	1.25*	--	--	--	0.015*	La-0.03
HAYNES® 214® alloy	N07214	75	2*	16	0.5*	0.5*	3	0.2*	0.5*	4.5	0.5*	--	0.01*	Y-0.01, Zr-0.1*, Cb-0.15*
HAYNES® 230-W® alloy	N06231	57	5*	22	2	14	3*	0.4	0.5	0.3	0.1*	0.5*	0.003*	La-0.02
HAYNES® 242® alloy	N10242	65	<1	8	25	--	2*	0.8*	0.8*	0.5*	--	0.5*	0.006*	--
HAYNES® 244™ alloy	2444	60	1*	8	22.5	6	2*	0.1*	0.8*	0.5*	-	0.5*	0.006*	--
HAYNES® 282® alloy	2082**	57	10	20	8.5	--	1.5*	0.15*	0.3*	1.5	2.1	--	0.005	--
HAYNES® M418 alloy	N04060	69*	--	--	--	--	2.5*	1.3*	4*	1.3*	<3	<19	--	
HAYNES® 556® alloy	R30556	20	18	22	3	2.5	31	0.4	1	0.2	--	--	0.02*	Zr-0.02, La-0.02, Ta-0.6, Cb-0.3*
HAYNES® 625 alloy	N06625	62	1*	22	9	--	5*	0.5*	0.5*	0.4*	0.4*	0.5*	--	Cb & Ta-3.7
HAYNES® 718 alloy	N07718	52	<1	18	3	--	19	0.35*	0.35*	0.5	0.9	0.1*	0.0004	Cb+Ta-5
I-36 alloy	K93601	36	<0.1	<0.1	--	--	63	0.14	0.3	0	--	<0.1	--	
L605 alloy	R30605	10	51	20	<1	15	3*	0.4*	1.5	--	--	--	--	--
M-400 alloy	N04400	67*	0.2*	--	--	--	1.4*	0.2*	1*	<0.1	--	33*	--	
M-413 alloy	C71581	31	<0.1	-	-	-	0.6	<0.1	0.7	<0.1	0.3	68	-	
MULTIMET® alloy	R30155	20	20	21	3	2.5	30	<1	1.5	--	--	0.5*	--	Cb-1, N 0.15, Ta-0.05*
N 61 alloy	N02061	96	<0.1	<0.1	<0.1	--	<0.1	0.4*	0.4	0.4*	3	<0.1	--	Cb-<0.1, Ta-<0.1
NFE 258 alloy	W82002	56*	<0.1	<0.1	<0.1	--	43	0.1*	0.7	<0.1	<0.1	<0.1	--	
NIT 32 alloy	S20000	1.5	<0.1	18	0.2	<0.1	69	0.4	12	--	<0.1	0.2	--	Cb-<0.1, V-<0.1
NIT 50 alloy	S20000	12	0.3*	21	2	--	59	0.5*	5	--	--	0.4	--	Cb-.016, V-0.15
NIT 60 alloy	S21800	8	<0.1	16	0.2	<0.1	63	4	8	<0.1	<0.1	0.2	--	V-<0.1
MP35N alloy	R30035	37*	34*	20*	10*	<0.1	0.3*	0.1*	0.1*	<0.1	0.7*	<0.1	<0.1	
ULTIMET® alloy	R31233	9	54	26	5	2	3	0.3	0.8	--	--	--	--	N-0.08
17/7 PH alloy	S17700	8*	0.1*	16	0.5*	--	73	0.5*	1*	1*	<0.1	0.4*	--	
20 alloy	N08904	25	0.1	21	4.5	--	46	0.4*	2*	0.1	--	1.9	--	
20CB3 alloy	N08020	33	<0.1	20	3*	--	71	0.4*	2*	<0.1	<0.1	3.4	<0.1	Cb-.06*, V-<0.1, Ta-<0.1

Table 1 Structural Wire Products (continued)

AWS/UNS		Normal Composition, Weight Percent												
ALLOY	Alloy No.	Ni▲	Co▲	Cr▲	Mo	W	Fe	Si	Mn▲	Al▲	Ti	Cu▲	B	Others (V▲)
52 alloy	N14052	50	<0.1	<0.1	--	--	49	0.1	0.5*	<0.1	<0.1	<0.1	--	
72 alloy	N06072	55	<0.1	44	<0.1	--	0.3	<0.1	<0.1	0.2*	0.5	<0.1	<0.1	
80/20 alloy	N06003	78	<0.1	20	--	--	0.7	1.3	<0.1	0.2	--	<0.1	--	
80/20 CB alloy	N06003	77	--	19	--	--	0.7	1.3	0.3	--	--	--	--	Cb-0.8
95/5 alloy	N03301	94	<0.1	--	--	--	<0.1	0.5*	0.3	5	0.7*	0.1*	--	Cb-<0.1, Ta-<0.1
200 alloy	N02200	99.4	--	<0.1	<0.1	--	0.2	<0.1	<0.1	--	<0.1	<0.1	--	
202 alloy	S20200	5*	--	18*	--	--	69*	0.6*	8	--	--	--	--	
214W alloy	N07214	<70	2*	<17	0.5*	0.5*	<4	0.2*	0.5*	<5	0.5*	--	0.004*	Cb 0.15*; Y<0.04; Zir 0.02*
302 alloy	S30200	8	--	18	0.3*	--	72	0.6*	1.8*	--	--	0.4*	--	
302 HQ alloy	S30430	9	--	17	--	--	70	0.5	0.7	--	--	3	--	
302 MO alloy	S30200	9	0.1	17	1.3	--	71	0.5	1.2	<0.1	--	0.1	--	
302 N alloy	S30200	9	--	18	--	--	70	0.6*	1.9	--	--	0.4	--	
302 NC alloy	S30200	8	--	17	<0.1	<0.1	74	0.4	0.3	<0.1	<0.1	<0.1	<0.1	V-0.1, Ta-<0.1
302 V alloy	S30200	8	<0.1	18	0.4	--	72	0.4	1	<0.1	--	0.2	--	
304 alloy	S30400	9	--	18	0.3*	--	71	0.5*	1.8*	--	--	0.3*	--	
304 L alloy	S30403	9	0.2*	18	0.4*	--	70	0.7*	1.8*	<0.1	--	0.5*	--	Y-<0.1
304 V alloy	S30400	8	0.15	18	0.2*	--	72	0.6*	0.7*	--	--	0.3*	--	
305 alloy	S30500	12*	--	18	0.3*	--	68	0.5*	1.4*	--	--	0.4*	--	
308 L alloy	S30800	10	--	21	--	--	66	0.8	1.9	--	--	--	--	
316 alloy	S31600	10	--	17*	2	--	69	0.5*	1.5*	--	--	0.5*	--	
316 LVM alloy	S31603	15*	<0.1	18*	3*	<0.1	62	0.5*	1.7	<0.1	<0.1	0.3*	<0.1	Cb-<0.1; V-0.3*;
316 L alloy	S31603	10	--	16	2	--	70	0.5*	1.5*	--	--	<0.1	--	
320 alloy	N08020	33	<0.1	20	3*	--	71	0.4*	2*	<0.1	<0.1	3.4	<0.1	
347 alloy	S34700	9	<0.1	17	0.3	--	70	0.6	1.5	<0.1	<0.1	0.2	<0.1	Cb-0.6, V-<0.1, Ta-<0.1
416 alloy	S41600	0.3*	--	13	<0.1	--	85	0.5*	0.9*	<0.1	--	0.1	--	
420H Stainless Steel	S42080	0.5*	--	<14	0.75*	--	82	0.5*	<0.6	--	--	0.75*	--	
420 alloy	S42000	0.1	--	13	--	--	86	0.2	0.5*	<0.1	--	0.1	--	
420 VMH alloy	S42000	0.3*	--	14*	<0.1	--	85	0.5*	0.4*	<0.1	--	<0.1	--	
420 VML alloy	S42000	0.2*	--	14*	<0.1	--	85	0.5	0.4	<0.1	--	<0.1	--	
420 DVM alloy	S42000	0.3*	--	14*	<0.1	--	85	0.5*	0.4*	<0.1	--	<0.1	--	
420 NWH alloy	S42000	0.3*	--	14*	<0.1	--	85	0.5*	0.4*	<0.1	--	<0.1	--	

Table 1 Structural Wire Products (continued)  
Normal Composition, Weight Percent

ALLOY	AWS/UNS	Normal Composition, Weight Percent												
	Alloy No.	Ni▲	Co▲	Cr▲	Mo	W	Fe	Si	Mn▲	Al▲	Ti	Cu▲	B	Others (V▲)
430 alloy	S43000	0.2*	--	17	<0.1	--	82	0.5*	0.5*	<0.1	--	0.1	--	
455 alloy	S45500	8	--	11	<0.1	--	77	<0.1	<0.1	--	1.2	2.2	--	Cb-0.2
600 alloy	N06600	74	0.05*	16	0.3	<0.1	9	0.4*	0.8	0.2	0.3*	0.02*	--	
601 alloy	N06601	60	--	23	--	--	16	0.3*	0.6	1.5	0.3	<0.1	0.003	
622 alloy	N06022	52	2.5*	<23	14	<3.5	<3	0.08*	0.05*	--	--	--	--	V 0.35*;
800 alloy	N08800	32	0.2*	19.5	0.2*	--	46*	0.8*	1.0	0.6*	0.5	0.2*	--	
825 alloy	N08825	41*	0.06*	23*	3*	--	31*	0.3*	0.6*	0.1	1*	2.5*	--	
875 alloy	--	--	--	22*	--	--	71	0.3*	0.2*	6*	--	<0.1	--	

(>) Reportable ingredients per Section 313 of SARA - See Section 15 for additional information. XX\* - indicates maximum value. XX<sup>b</sup> - indicates minimum value. XX\*\* - Haynes metal No.

HAYNES and HASTALLOY are registered trademarks of Haynes International, Inc.

**Table 2 Product Hazard Rating**  
**Hazardous Materials Identification System (HMIS)**  
**H = Health Rating F = Flammability Rating R = Reactivity Rating**

Alloy	Solid Article				Metal Dust				Metal Oxide Fume		
	H	F	R		H	F	R		H	F	R
HASTELLOY® HYBRID-BC1® alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® B-3 alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® C-4 alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® C-22® alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® C-22HS® alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® C-86 alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® C-276 alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® C-2000® alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® G-30® alloy	0	0	0		2*	2	0		3*	2	0
HASTELLOY® G-35® alloy	0	0	0		2*	2	0		3*	0	0
HASTELLOY® N alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® S alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® X alloy	0	0	0		2*	1	0		3*	0	0
HASTELLOY® W alloy	0	0	0		2*	1	0		3*	0	0
HAYNES® C-263 alloy	0	0	0		2*	2	0		3*	2	0
HAYNES® GTD 222 alloy	0	0	0		2*	2	0		3*	2	0
HAYNES® HR-120® alloy	0	0	0		2*	1	0		3*	0	0
HAYNES® HR-160® alloy	0	0	0		2*	2	0		3*	2	0
HAYNES® Waspaloy alloy	0	0	0		2*	2	0		3*	2	0
HAYNES® HR-224® alloy	0	0	0		2*	1	0		3*	0	0
HAYNES® HR-235™ alloy	0	0	0		2*	1	0		3*	0	0
HAYNES® NS-163® alloy	0	0	0		2	2	0		3*	2	0
HAYNES® X-750 alloy	0	0	0		2*	1	0		3*	0	0
HAYNES® 25 alloy	0	0	0		2*	2	0		3*	2	0
HAYNES® 92 alloy	0	0	0		2*	2	0		3*	0	0
HAYNES® 188 alloy	0	0	0		2*	2	0		3*	0	0
HAYNES® 214® alloy	0	0	0		2*	1	0		3*	0	0

**Table 2 Product Hazard Rating (continued)**  
**Hazardous Materials Identification System (HMIS)**  
**H = Health Rating F = Flammability Rating R = Reactivity Rating**

Alloy	Solid Article				Metal Dust				Metal Oxide Fume		
	H	F	R		H	F	R		H	F	R
HAYNES® 230-W® alloy	0	0	0		2*	1	0		3*	0	0
HAYNES® 242® alloy	0	0	0		2*	1	0		3*	0	0
HAYNES® 244™ alloy	0	0	0		2*	1	0		3*	0	0
HAYNES® 282® alloy	0	0	0		2*	2	0		3*	2	0
HAYNES® M-418 alloy	0	0	0		2*	0	0		3*	0	0
HAYNES® 556® alloy	0	0	0		2*	1	0		3*	1	0
HAYNES® 625 alloy	0	0	0		2*	0	0		3*	0	0
HAYNES® 718 alloy	0	0	0		2*	0	0		3*	0	0
I-36 alloy	0	0	0		2*	0	0		2*	0	0
L605 alloy	0	0	0		2	2	0		2*	0	0
M-400 alloy	0	0	0		2*	0	0		2*	0	0
M-413 alloy	0	0	0		2*	0	0		2*	0	0
MULTIMET® alloy	0	0	0		2*	1	0		3*	0	0
N 61 alloy	0	0	0		2*	0	0		2*	0	0
NFE 258 alloy	0	0	0		2*	0	0		2*	0	0
NIT 32 alloy	0	0	0		2	0	0		3*	0	0
NIT 50 alloy	0	0	0		2	0	0		3*	0	0
NIT 60 alloy	0	0	0		2	0	0		3*	0	0
MP35N alloy	0	0	0		2*	2	0		3*	0	0
ULTIMET® alloy	0	0	0		2*	2	0		2*	1	0
17/7 PH alloy	0	0	0		2	0	0		3*	0	0
20 alloy	0	0	0		2*	2	0		3*	0	0
20 CB 3 alloy	0	0	0		2*	0	0		3*	0	0
52 alloy	0	0	0		2*	0	0		2*	0	0
72 alloy	0	0	0		2*	0	0		3*	0	0
80/20 alloy	0	0	0		2*	0	0		3*	0	0
80/20 CB alloy	0	0	0		2*	0	0		3*	0	0
95/5 alloy	0	0	0		2*	0	0		2*	0	0
200 alloy	0	0	0		2*	0	0		2*	0	0

**Table 2 Product Hazard Rating (continued)**  
**Hazardous Materials Identification System (HMIS)**  
**H = Health Rating F = Flammability Rating R = Reactivity Rating**

Alloy	Solid Article				Metal Dust				Metal Oxide Fume		
	H	F	R		H	F	R		H	F	R
202 alloy	0	0	0		2*	0	0		3*	0	0
214W alloy	0	0	0		2*	1	0		3*	0	0
302 alloy	0	0	0		2*	0	0		3*	0	0
302 HQ alloy	0	0	0		2*	0	0		3*	0	0
302 MO alloy	0	0	0		2*	0	0		3*	0	0
302 N alloy	0	0	0		2*	0	0		3*	0	0
302 NC alloy	0	0	0		2*	0	0		3*	0	0
302 V alloy	0	0	0		2*	0	0		3*	0	0
304 alloy	0	0	0		2*	0	0		3*	0	0
304 L alloy	0	0	0		2*	0	0		3*	0	0
304 V alloy	0	0	0		2*	0	0		3*	0	0
305 alloy	0	0	0		2*	0	0		3*	0	0
308 L alloy	0	0	0		2*	0	0		3*	0	0
316 alloy	0	0	0		2*	0	0		3*	0	0
316 LVM alloy	0	0	0		2*	0	0		3*	0	0
316 L alloy	0	0	0		2*	0	01		3*	0	0
320 alloy	0	0	0		2*	0	0		3*	0	0
347 alloy	0	0	0		2*	0	0		3*	0	0
416 alloy	0	0	0		2	0	0		3*	0	0
420 alloy	0	0	0		2	0	0		3*	0	0
420H Stainless Steel	0	0	0		2	0	0		3*	0	0
420 VMH alloy	0	0	0		2	0	0		3*	0	0
420 VML alloy	0	0	0		2	0	0		3*	0	0
420 DVM alloy	0	0	0		2	0	0		3*	0	0
420 NWH alloy	0	0	0		2	0	0		3*	0	0
430 alloy	0	0	0		2	0	0		3*	0	0
455 alloy	0	0	0		2	0	0		3*	0	0
600 alloy	0	0	0		2*	0	0		3*	0	0
601 alloy	0	0	0		2*	0	0		3*	0	0
622 alloy	0	0	0		2*	0	0		3*	0	0

**Table 2 Product Hazard Rating (continued)**  
**Hazardous Materials Identification System (HMIS)**  
**H = Health Rating    F = Flammability Rating    R = Reactivity Rating**

Alloy	Solid Article				Metal Dust				Metal Oxide Fume		
	H	F	R		H	F	R		H	F	R
800 alloy	0	0	0		2*	0	0		3*	0	0
825 alloy	0	0	0		2*	0	0		3*	0	0
875 alloy	0	0	0		2	0	0		3*	0	0

As a solid article, all Haynes alloys are rated 0 for health, flammability, and reactivity. Metal dust may be created by grinding operations. Metal oxide fume may be created during welding, thermal cutting, or melting operations.

Note: Ratings applicable for the metal oxide components of each product. Metal oxides are typically found in welding fume.

\* = Chronic health effects, see Table 4. HAYNES and HASTELLOID are trademarks of Haynes International, Inc.

Summary of Hazardous Material Information System (HMIS) rating numbers:

H = Health Hazard rating; 0 = minimal hazard; 1 = slight hazard; 2 = moderate hazard; 3 = serious hazard; 4 = severe hazard

F = Flammability hazard rating; 0 = minimal hazard; 1 = slight hazard; 2 = moderate hazard; 3 = serious hazard; 4 = severe hazard

R = Reactivity hazard rating; 0 = minimal hazard; 1 = slight hazard; 2 = moderate hazard; 3 = serious hazard; 4 = severe hazard



Table 3 Exposure Limits for Potentially Hazardous Constituents in Structural Wire

Metal or Chemical, Symbol	CAS Number	Exposure Limits as 8-hour TWA (as mg/m <sup>3</sup> )	
		OSHA - Permissible Exposure Limit (PEL) <sup>(1)</sup>	ACGIH - Threshold Limit Value (TLV®) <sup>(1)</sup>
Aluminum (Al/Al <sub>2</sub> O <sub>3</sub> )	7429-90-5/ 1344-28-1	Aluminum Oxide as Al: 15, total Aluminum Oxide as Al: 5, Respirable	Welding Fume as Al: 10
Barium compounds (Ba X)	7440-39-3	Soluble compounds as Ba: 0.5	Soluble compounds as Ba: 0.5
Boron Oxide (B <sub>2</sub> O <sub>3</sub> )	1303-86-2	Oxide Dust Total: 15	Oxide Dust Total: 10
Calcium (Ca)	7440-70-2	None	None
Calcium Oxide (CaO)	1305-78-8	5	2
Carbon Monoxide <sup>(2)</sup> (CO)	630-08-0	55 (50 ppm)	29 (25 ppm)
Chromium VI Soluble Compounds	(3)	0.005	0.05 (as Cr)
Chromium VI Insoluble Compounds	(3)	0.005	0.01(as Cr)
Chromium oxide Cr III (Cr <sub>2</sub> O <sub>3</sub> )	1308-38-9	0.5 (as Cr)	0.5 (as Cr)
Chromium oxide Cr II (CrO)	12018-00-7	0.5 (as Cr)	-
Chromium metal (Cr)	7440-47-3	1 (as Cr)	0.5 (as Cr)
Cobalt (Co) and inorganic compounds	7440-48-4	0.1 metal dust and fume (as Co)	0.02 (as Co)
Columbium (Niobium) (Cb/Cb <sub>2</sub> O <sub>8</sub> , Nb/Nb <sub>2</sub> O <sub>8</sub> )	7440-03-1/ 1313-96-8	None	None
Copper oxide fume (CuO)	1317-38-0	0.1 (as Cu)	0.2 (as Cu)
Copper (Cu)	7440-50-8	1 (as Cu)	1 (as Cu)
Iron oxide (dust and fume) (Fe <sub>2</sub> O <sub>3</sub> )	1309-37-1	10 (as Fe)	5 <sup>(5)</sup> (as Fe)
Lanthanum (La)	7439-91-0	None	None
Lithium (Li/Li <sub>2</sub> O)	7439-92-2/ 12057-24-8	None	1 (as Li <sub>2</sub> O) (ceiling) <sup>(4), (6)</sup>
Magnesium (Mg)	7439-95-4	None	None
Magnesium Oxide (MgO)	1309-48-4	Fume as MgO: 15	Fume as MgO: 10 <sup>(7)</sup>
Manganese (Mn, MnO)	7439-96-5	5 (ceiling) <sup>(4)</sup> (as Mn)	0.02 (as Mn)
Molybdenum compounds (Mo X)	7439-98-7	Soluble Compounds as Mo: 5	Soluble Compounds as Mo: 0.5 <sup>(5)</sup> Insoluble Compounds as Mo: 3 <sup>(5)</sup> ; 10 <sup>(7)</sup>
Nickel (Ni, NiX)	7440-02-0	1 (elemental, soluble and insoluble compounds) (as Ni)	1.5 <sup>(7)</sup> elemental, 0.1 <sup>(7)</sup> soluble, 0.2 <sup>(7)</sup> insoluble compounds as Ni

Table 3 Exposure Limits for Potentially Hazardous Constituents in Structural Wire (continued)

Metal or Chemical, Symbol	CAS Number	Exposure Limits as 8-hour TWA (as mg/m <sup>3</sup> )	
		OSHA - Permissible Exposure Limit (PEL) <sup>(1)</sup>	ACGIH - Threshold Limit Value (TLV <sup>®</sup> ) <sup>(1)</sup>
Nitric Oxide <sup>(2)</sup> (NO)	10102-43-2	30	31
Nitrogen Dioxide <sup>(2)</sup> (NO <sub>2</sub> )	10102-44-2	9 (ceiling)	5.6; 9.4 (STEL) <sup>(8)</sup>
Ozone <sup>(2)</sup> (O <sub>3</sub> )	10028-15-6	0.2 (0.1 ppm)	0.1 (0.05 ppm), Heavy workload <sup>(9)</sup>
Silicon (Si)	7440-21-3	Total Dust: 15, Respirable Dust: 5	None
Strontium (Sr/SrO)	7440-24-6/ 1314-11-0	None	None
Tantalum (Ta)	7440-25-7	Metal and Oxide Dust: 5	Metal and Oxide Dust as Ta: 5
Titanium Dioxide (TiO <sub>2</sub> )	13463-67-7	15	10
Titanium (Ti)	7440-32-6	None	None
Tungsten (W) compounds	7440-33-7	None	Insoluble compounds as W: 5; 10 (STEL) <sup>(8)</sup> Soluble compounds as W: 1; 3 (STEL) <sup>(8)</sup>
Vanadium Pentoxide (V <sub>2</sub> O <sub>5</sub> )	1314-62-1	0.5 ceiling - respirable dust 0.1 ceiling - fume	0.05 Respirable Dust or Fume <sup>(5)</sup>
Yttrium (Y)	7440-65-5	1	Metal and Compounds as Y: 1
Zirconium compounds (Zr X)	7440-67-7	Compounds as Zr: 5	Zr Metal and Compounds as Zr: 5; 10 (STEL) <sup>(8)</sup>

(1) All limits are Total Dust unless indicated otherwise.

(2) Gases generated by arc welding processes.

(3) Varies with compound.

(4) Ceiling limit - shall not be exceeded instantaneously.

(5) Respirable fraction of particulate - refer to the ACGIH-TLV<sup>®</sup> booklet for a definition.

(6) Workplace Environmental Exposure Levels (WEEL), published by the American Industrial Hygiene Association.

(7) Inhalable fraction of particulate - refer to the ACGIH-TLV<sup>®</sup> booklet for a definition.

(8) STEL = Short-term exposure limit - A 15-minute TWA exposure limit.

(9) See additional TLV<sup>®</sup> listings for moderate or light workloads.

(10) National Institute for Occupational Safety and Health (NIOSH) Recommended Exposure Limit (REL).

Table 4 Health Hazards

The following table shows the compounds and gases which have been discussed previously, and which may be encountered, their names and formulas, their CAS number, and briefly describes possible known short term and long term health effects which may result from excessive exposure.

Name of Compound, Formula and CAS Number	On Any Carcinogens List? If So, Which Ones?	Health Effects Resulting from Excessive Exposure	
		Acute (Short Term)	Chronic (Long Term)
<b>Metal Dust and Welding Fumes</b>			
Welding Fumes (not otherwise classified) CAS No. - none	Yes IARC	May include metallic taste, nausea, tightness of chest, fever, dizziness, dryness or irritation of eyes, nose or throat	Excessive levels may cause bronchial asthma, lung fibrosis, pneumoconiosis or siderosis.
Hexavalent Chromium (Cr VI)	Yes IARC NTP OSHA	Inhalation and Skin Contact: Irritation of mucous membranes	Inhalation: Perforation of the nasal septum. Increased incidence of lung cancer. Skin Contact: Skin ulceration, dermatitis.
Chromium Metal-Cr CAS No. 7740-47-3 Chromium oxide (Cr II) CrO CAS No. 12018-00-7 Chromium oxide (Cr III) Cr <sub>2</sub> O <sub>3</sub>	Yes IARC	Skin Contact: Allergic reactions (dermatitis) in some people.	None known.
Nickel-Ni CAS No. 7440-02-0 Nickel oxide-NiO CAS No. 1313-99-1	Yes IARC NTP	Inhalation: Respiratory irritation. Allergic reactions in some people. Metallic taste, nausea, tightness in chest, metal fume fever. Skin Contact: Contact dermatitis with permanent sensitization.	Inhalation: Chronic pulmonary irritation. Perforation of nasal septum. Increased incidence of lung and larynx cancer.
Cobalt-Co CAS No. 7440-48-4 Cobalt Oxide - CoO CAS no. 1307-96-6	No	Inhalation: Pulmonary irritant, cough. Eye Contact: Irritation, conjunctivitis Skin: Mild irritation sensitization, allergic dermatitis. Ingestion: Pain, nausea, vomiting, hypotension (low blood pressure).	Chronic exposure to cobalt is more dangerous than isolated exposures. Possible lung fibrosis and respiratory hypersensitivity. Heart disease, elevated red blood cell counts, chest pain and edema.
Copper-Cu CAS No. 7440-50-8 Copper oxide-CuO CAS No. 1317-38-0	No	Inhalation: Metal fume fever, muscle ache, respiratory irritant. Skin: Irritation, Ingestion: Nausea, vomiting, abdominal pain; large doses may cause stomach and intestine ulceration, and kidney and liver damage.	Mild dermatitis and degeneration of mucous membranes. Repeated inhalation can cause chrome respiratory disease.
Manganese-Mn CAS No. 7439-96-5 Manganese dioxide-as Mn for fume MnO <sub>2</sub> CAS No. 1313-13-9	No	Can include metal fume fever, dry throat, coughing, tight chest, low back pain, vomiting, fatigue, headache	Manganism. SENSITIVITY VARIES. Affects central nervous system. Muscular weakness, tremors, symptoms similar to Parkinson's disease. Exposed employees should get quarterly medical examinations for manganism.

Table 4 Health Hazards (continued)

Name of Compound, Formula and CAS Number	On Any Carcinogens List? If So, Which Ones?	Health Effects Resulting from Excessive Exposure	
		Acute (Short Term)	Chronic (Long Term)
Vanadium Pentoxide (V <sub>2</sub> O <sub>5</sub> )	No	Irritant to mucous membranes. Metallic taste, cough, throat and eye irritation, eczema.	Nasal catarrh, nose bleeds, chronic respiratory problems.
Iron-Fe CAS No. 7439-89-6 Iron Oxide-FeO CAS No. 1345-25-1 Iron Oxide-Fe <sub>2</sub> O <sub>3</sub> CAS No. 1309-37-1 Iron Oxide-Fe <sub>3</sub> O <sub>4</sub> CAS No. 1309-38-2	No	Probably none, except as nuisance dust.	Possible siderosis if exposures are excessive and long term. Regarded as benign. Lungs clear gradually after exposure is ended.