

HASTELLOY® C-2000® Alloy

Hydrobromic Acid

Conc. Wt.%	50°F	75°F	100°F	125°F	150°F	175°F	200°F	225°F	Boiling
	10°C	24°C	38°C	52°C	66°C	79°C	93°C	107°C	
2.5	-	-	-	-	<0.01	-	0.01	-	0.01
5	-	-	-	-	<0.01	-	0.01	-	0.15
7.5	-	-	-	-	-	<0.01	<0.01	-	0.58
10	-	-	-	-	<0.01	<0.01	0.34	-	1.71
15	-	-	-	-	-	0.1	0.94	-	-
20	-	-	-	-	<0.01	0.61	0.86	-	2.52
25	-	-	<0.01	0.15	0.3	0.53	0.91	-	-
30	-	-	0.06	0.2	0.29	0.48	0.91	-	-
40	-	-	0.07	0.13	0.18	0.32	0.6	-	-


All corrosion rates are in millimeters per year (mm/y); to convert to mils (thousandths of an inch) per year, divide by 0.0254.

Data are from Corrosion Laboratory Jobs 71-97, 26-99, 49-99, 27-02, and 37-02.

All tests were performed in reagent grade acids under laboratory conditions; field tests are encouraged prior to industrial use.

HASTELLOY® C-2000® Alloy

Iso-Corrosion Diagram for C-2000 Alloy in Hydrobromic Acid



When using this data, please refer to our disclaimer located at www.haynesintl.com