

## HASTELLOY® G-35® Alloy

### Hydrobromic Acid

Conc. Wt.%	50°F	75°F	100°F	125°F	150°F	175°F	200°F	225°F	Boiling
	10°C	24°C	38°C	52°C	66°C	79°C	93°C	107°C	
2.5	-	-	-	-	<0.01	-	<0.01	-	<0.01
5	-	-	-	-	<0.01	-	<0.01	-	<0.01
7.5	-	-	-	-	<0.01	-	<0.01	-	0.02
10	-	-	-	-	<0.01	<0.01	1.12	-	-
15	-	-	-	-	<0.01	0.41	1.89	-	-
20	-	-	-	<0.01	0.44	1.12	-	-	-
25	-	-	-	-	-	-	-	-	-
30	-	0.01	0.14	0.26	0.46	0.84	-	-	-
40	-	-	0.1	0.17	0.31	0.48	-	-	-

All corrosion rates are in millimeters per year (mm/y); to convert to mils (thousandths of an inch) per year, divide by 0.0254.

Data are from Corrosion Laboratory Job 17-04.

All tests were performed in reagent grade acids under laboratory conditions; field tests are encouraged prior to industrial use.

# HASTELLOY® G-35® Alloy

## Iso-Corrosion Diagram for G-35 Alloy in Hydrobromic Acid

