

HAYNES® 625SQ® alloy

Principal Features

HAYNES® 625SQ® alloy (UNS N06626) is a solid-solution strengthened superalloy. It is a modification of HAYNES® 625 alloy developed to enhance resistance to fatigue at temperatures up to approximately 1200°F (649°C). The alloy composition is tightly controlled to very low levels of carbon, silicon, and nitrogen.

Primary melting is by vacuum induction melting, followed by consumable electrode practice using electroslag remelting. During processing, the grain size is controlled to ASTM #5 or finer.

HAYNES® 625SQ® alloy is readily fabricated and welded using practices common to HAYNES® 625 alloy. HAYNES® 625SQ® alloy sheet and strip find application in aerospace, automotive, and chemical process industry bellow, expansion joints, and fabrications where fatigue resistance, strength, and corrosion resistance are required.

Nominal Composition

Weight %

Nickel:	62 Balance
Cobalt:	1 max.
Iron:	5 max.
Chromium:	21
Molybdenum:	9
Columbium + Tantalum:	3.7
Manganese:	0.5 max.
Silicon:	0.15 max.
Nitrogen:	0.02 max.
Aluminum:	0.4 max.
Titanium:	0.4 max.
Carbon:	0.03 max.

Physical Properties

Physical Property	British Units		Metric Units	
Density	RT	0.305lb/in ³	RT	8.44 g/cm ³
Melting Range	2350-2460°F	-	1290-1350°C	-
Electrical Resistivity	400°F	52.8 μohm-in	200°C	134.0 μohm-cm
	800°F	53.5 μohm-in	400°C	135.6 μohm-cm
	1000°F	54.3 μohm-in	600°C	137.9 μohm-cm
	1200°F	54.3 μohm-in	700°C	137.5 μohm-cm
	1400°F	53.9 μohm-in	800°C	136.5 μohm-cm
	1600°F	53.5 μohm-in	900°C	135.6 μohm-cm
	1800°F	53.1 μohm-in	1000°C	134.8 μohm-cm
Thermal Conductivity	800°F	109 Btu-in/ft ² -hr-°F	400°C	15.3 W/m-°C
	1000°F	121 Btu-in/ft ² -hr-°F	600°C	18.3 W/m-°C
	1200°F	132 Btu-in/ft ² -hr-°F	700°C	19.8 W/m-°C
	1400°F	144 Btu-in/ft ² -hr-°F	800°C	21.5 W/m-°C
	1600°F	158 Btu-in/ft ² -hr-°F	900°C	23.4 W/m-°C
	1800°F	175 Btu-in/ft ² -hr-°F	1000°C	25.6 W/m-°C
Mean Coefficient of Thermal Expansion	70-800°F	7.7 μin/in-°F	20-500°C	14.2 μm/m-°C
	70-1000°F	8.0 μin/in-°F	20-600°C	14.8 μm/m-°C
	70-1200°F	8.2 μin/in-°F	20-700°C	15.4 μm/m-°C
	70-1400°F	8.6 μin/in-°F	20-800°C	16.1 μm/m-°C
	70-1600°F	9.2 μin/in-°F	20-900°C	16.8 μm/m-°C
	70-1800°F	9.6 μin/in-°F	20-1000°C	17.4 μm/m-°C
Dynamic Modulus of Elasticity	70°F	30.2 x 10 ⁶ psi	20°C	208 GPa
	400°F	28.8 x 10 ⁶ psi	200°C	199 GPa
	800°F	26.7 x 10 ⁶ psi	400°C	186 GPa
	1000°F	25.6 x 10 ⁶ psi	600°C	171 GPa
	1200°F	24.3 x 10 ⁶ psi	700°C	163 GPa
	1400°F	22.8 x 10 ⁶ psi	800°C	153 GPa
	1600°F	21.2 x 10 ⁶ psi	900°C	142 GPa
	1800°F	18.7 x 10 ⁶ psi	1000°C	126 GPa

RT=Room Temperature

Tensile Properties

Sheet (AMS 5879)

Test Temperature		0.2% Yield Strength		Ultimate Tensile Strength		Elongation
°F	°C	ksi	MPa	ksi	MPa	%
RT	RT	65.5	452	129.9	895	51.7
600	316	51.1	353	117.4	809	64.1
800	427	49.1	339	112.6	776	60.9
1000	538	49.9	344	112.5	776	60.5
1200	649	46.9	323	114.2	787	81.4
1300	704	44.4	306	93.7	646	103.9
1400	760	46.9	323	72.1	497	88.8

RT= Room Temperature

Heat Treatment

Sheet and Strip, AMS 5879

1600°F (871°C) Minimum/Bright Anneal

Specifications and Codes

Specifications

HAYNES® 625SQ® alloy (N06626)	
Sheet, Plate & Strip	AMS 5879 ASME Code Case 2276
Billet, Rod & Bar	-
Coated Electrodes	-
Bare Welding Rods & Wire	-
Seamless Pipe & Tube	-
Welded Pipe & Tube	ASME Code Case No. 2276 P= 43
Fittings	ASME Code Case No. 2276 P= 43
Forgings	-
DIN	-
Others	-

Codes

HAYNES® 625SQ® alloy (N06626)			
ASME	Section I	-	
	Section III	Class 1	-
		Class 2	-
		Class 3	-
	Section IV	HF-300.2	-
	Section VIII	Div. 1	Code Case 2276 800°F (427°C) ¹
		Div. 2	-
	Section XII	-	
	B16.5	-	
	B16.34	-	
	B31.1	-	
	B31.3	-	

¹Approved material forms: Sheet, fittings, welded pipe/tube

Disclaimer:

Haynes International makes all reasonable efforts to ensure the accuracy and correctness of the data in this document but makes no representations or warranties as to the data's accuracy, correctness or reliability. All data are for general information only and not for providing design advice. Alloy properties disclosed here are based on work conducted principally by Haynes International, Inc. and occasionally supplemented by information from the open literature and, as such, are indicative only of the results of such tests and should not be considered guaranteed maximums or minimums. It is the responsibility of the user to test specific alloys under actual service conditions to determine their suitability for a particular purpose.

For specific concentrations of elements present in a particular product and a discussion of the potential health effects thereof, refer to the Safety Data Sheets supplied by Haynes International, Inc. All trademarks are owned by Haynes International, Inc., unless otherwise indicated.